

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
9 February 2006 (09.02.2006)

PCT

(10) International Publication Number  
**WO 2006/014597 A1**(51) International Patent Classification<sup>7</sup>: **A61K 6/00**(21) International Application Number:  
PCT/US2005/024291

(22) International Filing Date: 7 July 2005 (07.07.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/586,326 8 July 2004 (08.07.2004) US  
60/600,558 11 August 2004 (11.08.2004) US(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US];  
3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CRAIG, Bradley D.**, [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **LEE, Robert**, [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **ABUELYAMAN, Ahmed S.**, [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **FALSAFI, Afshin**, [IR/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **AASEN, Steven M.**, [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **OXMAN, Joel D.**, [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).(74) Agents: **EDMAN, Sean J.**, et al.; 3M Center, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH,

GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

## Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: DENTAL METHODS, COMPOSITIONS, AND KITS INCLUDING ACID-SENSITIVE DYES

(57) Abstract: Methods and compositions including an aqueous liquid that includes an acid-sensitive dye are disclosed for use in dental and orthodontic procedures. The aqueous liquid can be useful for providing a visible color change to indicate contact with acidic materials including, for example, etching compositions, self-etching adhesives, and self-adhesive compositions.

WO 2006/014597 A1

## DENTAL METHODS, COMPOSITIONS, AND KITS INCLUDING ACID-SENSITIVE DYES

### BACKGROUND

For a variety of dental procedures, it is important, but often difficult, for a practitioner to be able to detect materials and surfaces that have come in contact with acidic materials. For example, etching compositions are acidic materials that are routinely applied to a surface of a dental structure as part of a variety of bonding procedures, and it is important for the practitioner to be able to readily determine which surfaces have had an etching composition applied thereto. However, it is oftentimes difficult for the practitioner to visually detect which surfaces have had an etchant applied thereto.

Recent advances in dentistry have provided dental adhesives and compositions that are self-etching and thus, do not require a separate etching step. Some of these self-etching adhesives and compositions may be, and even preferably are, applied to a wet surface of a dental structure. In some cases it may be difficult to determine which surfaces have been properly wetted before application of the self-etching adhesive or composition. In some cases, the surface of the dental structure will not be properly etched if the surface was not properly wetted before application of the self-etching adhesive or composition.

There exists a need for methods and compositions to visually indicate surfaces and materials that are contacted with acidic materials.

### SUMMARY OF THE INVENTION

In one aspect, the present invention provides a method for applying an etching composition to a dental structure. The method includes: wetting a surface of a dental structure with a liquid including an acid-sensitive dye and water; and applying an etching composition to at least a portion of the wet dental

structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the etching composition applied thereon.

5 In another aspect, the present invention provides a method for applying a self-etching adhesive to a dental structure. The method includes: wetting a surface of a dental structure with a liquid including an acid-sensitive dye and water; and applying a self-etching adhesive to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-etching  
10 adhesive applied thereon. Preferably, the visually observable color change is from colored to essentially colorless.

In another aspect, the present invention provides a method for applying a self-adhesive composition to a dental structure. The method includes: wetting a surface of a dental structure with a liquid including an acid-sensitive dye and  
15 water; and applying a self-adhesive composition to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-adhesive composition applied thereon. Preferably, the visually observable color change is from colored to essentially colorless.

20 Optionally, the self-adhesive composition can be provided as a precoated orthodontic appliance by a manufacturer, and the precoated orthodontic appliance can be applied to the wet dental structure surface. Exemplary orthodontic appliances include, for example, brackets, buccal tubes, bands, cleats, buttons, lingual retainers, bite blockers, and combinations thereof.

25 Alternatively, the self-adhesive composition can be applied to a surface of an orthodontic appliance by a practitioner to provide a coated orthodontic appliance, and the coated orthodontic appliance can be applied to the wet dental structure surface. Optionally, the self-adhesive composition can be provided on an adhesive transfer area of a substrate, and the self-adhesive composition can be  
30 transferred from the adhesive transfer area of the substrate for applying to the orthodontic appliance.

In another aspect, the present invention provides a method of bonding a dental material to a dental structure. The method includes: wetting a surface of a dental structure with a liquid including an acid-sensitive dye and water; applying a self-etching adhesive to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-etching adhesive applied thereon; drying the dental structure surface to form a first adhesive layer thereon; optionally applying a second adhesive over the first layer to form a second adhesive layer thereon; applying a dental material to the dental structure surface having the first adhesive layer and optionally the second adhesive layer thereon; and hardening at least one of the adhesive layers under conditions effective to form a bond between the dental material and the dental structure. Preferably, the visually observable color change is from colored to essentially colorless. Preferably, the adhesive is hardened under conditions effective to form a bond between the dental material and the dental structure of at least 7 MPa. The adhesive can be hardened before, during, or after applying the dental material. The second adhesive can be the same as the self-etching adhesive or different than the self-etching adhesive. The dental material can include, for example, a dental restorative, an orthodontic adhesive, or an orthodontic appliance.

In another aspect, the present invention provides a method of restoring a dental structure. The method includes: wetting a surface of a dental structure with a liquid including an acid-sensitive dye and water; applying a self-adhesive composition to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-adhesive composition applied thereon; and hardening the self-adhesive composition under conditions effective to form a bond between the hardened composition and the dental structure of at least 7 MPa. Preferably, the self-adhesive composition includes at least 40% by weight filler. Preferably, the visually observable color change is from colored to essentially colorless.

In another aspect, the present invention provides a method of adhering an orthodontic appliance to a tooth. In one embodiment, the method includes:

wetting a surface of a tooth with a liquid including an acid-sensitive dye and water; applying a self-adhesive composition to at least a portion of the wet tooth surface under conditions effective to cause a visually observable color change in the portion of the tooth surface having the self-adhesive composition applied thereon; applying an orthodontic appliance to the tooth surface having the self-adhesive composition applied thereon; and hardening the self-adhesive composition under conditions effective to form a bond between the orthodontic appliance and the tooth.

In another embodiment, the method includes: wetting a surface of a tooth with a liquid including an acid-sensitive dye and water; applying an orthodontic appliance having a self-adhesive composition thereon to at least a portion of the wet tooth surface under conditions effective to cause a visually observable color change in the portion of the tooth surface having the orthodontic appliance and self-adhesive composition applied thereon; and hardening the self-adhesive composition under conditions effective to form a bond between the orthodontic appliance and the tooth. In some embodiments, the method further includes applying a self-adhesive composition to an orthodontic appliance to provide the orthodontic appliance having the self-adhesive composition thereon. In other embodiments, the orthodontic appliance having the self-adhesive composition thereon is provided as a precoated orthodontic appliance.

In another aspect, the present invention provides a multi-part dental composition including: a first part including an acid-sensitive dye; and a second part including an acid, wherein contacting the first part and the second part is effective to cause a color change.

In another aspect, the present invention provides a method for using a multi-part dental composition including contacting a first part including an acid-sensitive dye and a second part including an acid, wherein contacting is effective to cause a color change. Preferably, the color change is from colored to essentially colorless. Optionally, the second part includes a self-etching adhesive or a self-adhesive composition.

In another aspect, the present invention provides kits that include an acid-sensitive dye. In one embodiment, the kit includes: a liquid including an acid-

sensitive dye and water; and a dental etching composition. In another embodiment, the kit includes: a liquid including an acid-sensitive dye and water; and a self-etching dental adhesive. In another embodiment, the kit includes: a liquid including an acid-sensitive dye and water; and a self-adhesive dental composition.

### *Definitions*

As used herein, "adhesive" or "dental adhesive" refers to a composition used as a pre-treatment on a dental structure (e.g., a tooth) to adhere a "dental material" (e.g., "restorative," an orthodontic appliance (e.g., bracket), or an "orthodontic adhesive") to the dental structure. An "orthodontic adhesive" refers to a highly (generally greater than 40 % by weight) filled composition (more analogous to a "restorative material" than to a "dental adhesive") used to adhere an orthodontic appliance to a surface of a dental structure (e.g., tooth). Generally, the surface of the dental structure is pre-treated, e.g., by etching, priming, and/or applying an adhesive to enhance the adhesion of the "orthodontic adhesive" to the dental structure.

As used herein, a "restorative" or a "dental restorative" are used interchangeably and include, for example, cured or uncured composites such as glass ionomer cements and modified glass ionomer cements, fillings, sealants, inlays, onlays, crowns, bridges, and combinations thereof.

As used herein, a "filling" refers to a highly filled paste suitable for filling a substantial void in a tooth structure.

As used herein, a "non-aqueous" composition (e.g., an adhesive) refers to a composition in which water has not been added as a component. However, there may be adventitious water in other components of the composition, but the total amount of water does not adversely affect stability (e.g., the shelf-life) of the non-aqueous composition. Non-aqueous compositions preferably include less than 1% by weight, more preferably less than 0.5% by weight, and most preferably less than 0.1% by weight water, based on the total weight of the non-aqueous composition.

As used herein, a "self-etching" composition refers to a composition that bonds to a dental structure without pretreating the surface of the dental structure surface with an etchant. Preferably, a self-etching composition can also function as a self-primer wherein no separate etchant or primer are used.

5       As used herein, a "self-adhesive" composition refers to a composition that is capable of bonding to a dental structure without pretreating the surface of the dental structure with a primer or bonding agent. Preferably, a self-adhesive composition is also a self-etching composition wherein no separate etchant is used.

10       As used herein, "hardening" or "curing" a composition are used interchangeably and refer to polymerization and/or crosslinking reactions including, for example, photopolymerization reactions and chemical polymerization techniques (e.g., ionic reactions or chemical reactions forming radicals effective to polymerize ethylenically unsaturated compounds) involving  
15 one or more materials included in the composition.

As used herein, a "dental structure" refers to tooth structures (e.g., enamel, dentin, and cementum) and bone. As used herein, a "dental structure surface" or a "tooth surface" refers to an exposed surface of a dental structure or a tooth, respectively. The exposed surface may optionally include a material  
20 (e.g., a layer of material) on the dental structure or tooth.

As used herein, an "uncut" dental structure surface refers to a dental structure surface that has not been prepared by cutting, grinding, drilling, etc.

As used herein, an "unetched" dental structure surface refers to a tooth or bone surface that has not been treated with an etchant prior to application of a  
25 self-etching adhesive or a self-adhesive compositions of the present invention.

As used herein, an "etchant" refers to an acidic composition that is capable of fully or partially solubilizing (i.e., etching) a dental structure surface. The etching effect can be visible to the naked human eye and/or instrumentally detectably (e.g., by light microscopy). Typically, an etchant is applied to the  
30 dental structure surface for a period of about 10 to 30 seconds.

As used herein, a "wet" dental structure surface refers to a surface of a dental structure that has visible water present (i.e., visible to a naked human eye).

As used herein, a "dry" dental structure surface refers to a surface of a dental structure that has been dried (e.g., air dried) and does not have present visible water.

As used herein, "dental material" refers to a material that may be bonded to a dental structure and includes, for example, dental restoratives, orthodontic appliances, and/or orthodontic adhesives.

As used herein, a "surfactant" refers to a surface-active agent that modifies the nature of a surface (e.g., reduces the surface tension) and encompasses surface-active agents typically referred to as "wetting agents."

As used herein, "a" or "an" means "at least one" or "one or more" unless otherwise indicated.

## DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

In one exemplary embodiment, the present invention provides methods and compositions to visually indicate (or identify) a dental structure surface that has been contacted with an aqueous liquid, and further to visually indicate when that wet surface has been subsequently contacted with an acidic dental composition. Such results can be achieved by including an acid-sensitive dye in the aqueous liquid.

In other exemplary embodiments, the invention provides an acid-sensitive dye to indicate when components of a multi-component dental composition have been contacted or mixed. For example, one component (e.g., an aqueous liquid component) of a multi-component dental composition may include an acid-sensitive dye to visually indicate when that component has been contacted or mixed with another component or components of the multi-component dental composition.

Acid-sensitive dyes useful in the present invention are dyes that exhibit different colors (or lack of color) at different pH conditions. Useful acid-sensitive dyes include, for example, well-known pH indicator dyes. Typically,



such dyes are of low toxicity and are miscible or dispersable in liquids, preferably aqueous liquids (i.e., liquids that include water, preferably as the major component). Preferably such dyes are soluble in aqueous liquids, and more preferably form stable aqueous solutions.

5           Suitable acid-sensitive dyes useful in the present invention are well known to one of skill in the art and include, for example, Eosin dyes (e.g., Rose Bengal, Bromothymol Blue, Erythrosin B, and Eosin Y), azo dyes (Methyl Red and Methyl Orange), triarylmethane dyes, oxonol dyes, and phenolphthalein. Useful acid-sensitive dyes are frequently commercially available. *See, for*  
10 *example*, Floyd J. Green, *The Sigma-Aldrich Handbook of Stains, Dyes, and Indicators [with Transmission Spectrum Reference]*, Aldrich Chemical Co., Milwaukee, WI (1990) for exemplary acid-sensitive dyes. Exemplary preferred acid-sensitive dyes include Rose Bengal, Bromothymol Blue, Methyl Red, and Methyl Orange. A more preferred acid-sensitive dye is Rose Bengal.

15           Methods and compositions of the present invention include liquids that include an acid-sensitive dye and water (i.e., aqueous liquids). Preferably the acid-sensitive dye is dissolved in the aqueous liquid, thereby forming a solution of the acid-sensitive dye in the aqueous liquid. Preferably, the aqueous liquid includes at least 0.0001% by weight, more preferably at least 0.001% by weight,  
20 and most preferably at least 0.01% by weight, of an acid-sensitive dye, based on the total weight of the aqueous liquid. Preferably, the aqueous liquid includes at most 5% by weight, more preferably at most 2% by weight, and most preferably at most 1% by weight acid-sensitive dye, based on the total weight of the aqueous liquid.

25           Aqueous liquids including an acid-sensitive dye useful in the present invention exhibit at least one visually observable color change when the pH of the aqueous liquid is changed. Preferably, the aqueous liquids exhibit a visually observable color change when the pH of the aqueous liquid is changed to become more acidic. For certain specific embodiments (e.g., embodiments that  
30 include applying an etching composition to a dental structure), the aqueous liquid preferably exhibits a visually observable color change when the pH is changed from a pH greater than or equal to 5 to a pH less than or equal to 3.

The term "visually observable color change" is meant to include a change in color from colored to essentially colorless, a change in color from essentially colorless to colored, or a change from a first color to a second color, that is observable by a naked eye of a human observer under ordinary office lighting conditions. Preferably, a visually observable color change corresponds to a change in CIELAB color coordinates  $\Delta E$  units of at least 10, more preferably at least 20, and most preferably at least 30.

In addition to an acid-sensitive dye, aqueous liquids useful in the present invention can also optionally include stabilizers, buffers, surfactants, antibacterial agents, water-soluble monomers (e.g., polymerizable components), pH adjuster agents, thickeners, fluoride anions, fluoride releasing agents, and combinations thereof. In certain embodiments, an aqueous liquid including an acid-sensitive dye is applied to a dental structure in such a manner to impart a first color to the structure. Upon subsequent application of an acidic material (e.g., a dental etchant, a dental self-etching adhesive, or a dental self-adhesive composition) to the wet structure, the pH of the initially applied aqueous liquid including the acid-sensitive dye is lowered, thereby imparting a second color to the structure. Preferably, the first color is readily visible to an observer (e.g., a red, pink, orange, or blue color), whereas the second color is essentially colorless. As used herein, "essentially colorless" means that no color difference between the dental structure and the dental structure having the aqueous liquid applied thereto is observable by a naked eye of a human observer under ordinary office lighting conditions. Preferably, "essentially colorless" corresponds to a color difference between the dental structure and the dental structure having the aqueous liquid applied thereto in CIELAB color coordinates  $\Delta E$  units of at most 10, more preferably at most 6, and most preferably at most 3. At the end of the procedure, it is typically desirable that the dental structure remains essentially colorless, i.e., that no visually observable color returns to the dental structure surface over time.

Preferred acid-sensitive dyes are those that exhibit a color change from a first color (not essentially colorless) to essentially colorless (and more preferably colorless) upon lowering of the pH.

*SELF-ETCHING ADHESIVES*

Self-etching adhesives refer to adhesives that bond to a dental structure without pretreating the surface of the dental structure surface with an etchant.

5 Preferably, a self-etching adhesive can also function as a self-primer wherein no separate etchant or primer are used. Self-etching adhesives are well known to those of skill in the art and include, for example, those disclosed in U.S. Pat. No. 6,506,816 (Ario et al.); U.S. Pat. Application Publication No. 2004/0206932 A1 (Abuelyaman); U.S. Pat. Application Serial No. 10/916,168, filed August 11,  
10 2004; and U.S. Pat. Application Serial No. 10/916,169, filed August 11, 2004. Exemplary self-etching adhesives also include those available under the trade designation ADPER PROMPT L-POP from 3M ESPE (St. Paul, MN).

In one exemplary embodiment, the self-etching adhesive is a non-aqueous self-etching adhesive. The non-aqueous self-etching adhesive can  
15 include, for example, an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, and an initiator system. Exemplary acid-functionality includes carboxylic acid functionality includes phosphoric acid functionality, phosphonic acid functionality, sulfonic acid functionality, or combinations thereof. Optionally,  
20 the non-aqueous self-etching adhesive further includes a filler. Optionally, the non-aqueous self-etching adhesive further includes a surfactant. Exemplary non-aqueous self-etching adhesives are disclosed, for example, in U.S. Pat. Application Serial No. 10/916,168, filed August 11, 2004.

In another exemplary embodiment, the self-etching adhesive includes a  
25 water-in-oil emulsion (e.g., a microemulsion). Preferably, the emulsion is physically and/or chemically stable. The self-etching adhesive can include, for example, an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, an initiator system, and water. In some embodiments, the self-etching adhesive includes  
30 less than 30% by weight water. Exemplary acid-functionality includes carboxylic acid functionality includes phosphoric acid functionality, phosphonic acid functionality, sulfonic acid functionality, or combinations thereof.

Optionally, the self-etching adhesive further includes a filler. Optionally, the self-etching adhesive further includes a surfactant. Exemplary self-etching adhesives including a water-in-oil emulsion are disclosed, for example, in U.S. Pat. Application Serial No. 10/916,169, filed August 11, 2004.

5

### *SELF-ADHESIVE COMPOSITIONS*

Self-adhesive compositions refer to compositions that are capable of bonding to a dental structure without pretreating the surface of the dental structure with a primer or bonding agent. Preferably, a self-adhesive composition is also a self-etching composition wherein no separate etchant is used. Self-adhesive compositions are known to those of skill in the art and include, for example, those disclosed in U.S. Pat. Application Publication No. 2004/0110864 A1 (Hecht et al.) and U.S. Pat. Application Serial No. 10/916,240, filed August 11, 2004.

10

In one exemplary embodiment, the self-adhesive composition is a non-aqueous self-adhesive composition. The non-aqueous self-adhesive composition can include, for example, an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, an initiator system, and at least 40% by weight filler, based on the total weight of the non-aqueous self-adhesive composition. Exemplary acid functionality includes, for example, carboxylic acid functionality, phosphoric acid functionality, phosphonic acid functionality, sulfonic acid functionality, or combinations thereof. Optionally, the non-aqueous self-adhesive composition further includes a surfactant. Exemplary non-aqueous self-adhesive compositions are disclosed, for example, in U.S. Pat. Application Serial No. 10/916,240, filed August 11, 2004.

15

20

25

30

### *METHODS, COMPOSITIONS, AND KITS*

Aqueous liquids including an acid-sensitive dye as described herein are particularly useful in aiding the practitioner to determine whether a surface of a

dental structure has been properly wetted before application of a self-etching adhesive or self-adhesive composition thereto.

For example, a surface of a dental structure can be wetted with a liquid including an acid-sensitive dye and water prior to applying an etching  
5 composition, a self-etching adhesive, or a self-adhesive composition to at least a portion of the wet dental structure surface. The application of the etching composition, self-etching adhesive, or self-adhesive composition can cause a visually observable color change in the portion of the dental structure surface having the etching composition, self-etching adhesive, or self-adhesive  
10 composition applied thereon. Preferably, the visually observable color change is from colored to essentially colorless.

Optionally, a self-adhesive composition can be provided by a manufacturer as a precoated orthodontic appliance that is packaged in a suitable container, and the precoated orthodontic appliance can be applied by a  
15 practitioner to the wet dental structure surface. Exemplary orthodontic appliances include, for example, brackets, buccal tubes, bands, cleats, buttons, lingual retainers, bite blockers, and combinations thereof. Exemplary containers are well known in the art and are disclosed, for example, in U.S. Pat. Nos. 5,172,809 (Jacobs et al.), 6,089,861 (Kelly et al.) and U.S. Pat. Application  
20 Publication No. 2003/0196914 A1 (Tzou et al.).

Alternatively, a self-adhesive composition can be applied to a surface of an orthodontic appliance by a practitioner to provide a coated orthodontic appliance, and the coated orthodontic appliance can be applied to the wet dental structure surface. Optionally, the self-adhesive composition can be provided on  
25 an adhesive transfer area of a substrate, and the self-adhesive composition can be transferred from the adhesive transfer area of the substrate for applying to the orthodontic appliance. Exemplary substrates with transfer areas are described, for example, in U.S. Pat. No. 6,213,767 (Dixon et al.).

Further, the present invention can be useful for bonding a dental material  
30 to a dental structure. For example, a surface of a dental structure can be wetted with a liquid including an acid-sensitive dye and water prior to applying a self-etching adhesive to at least a portion of the wet dental structure surface. The

application of the self-etching adhesive can cause a visually observable color change in the portion of the dental structure surface having the self-etching adhesive applied thereon. Preferably, the visually observable color change is from colored to essentially colorless. The dental structure surface can be dried  
5 to form a first adhesive layer thereon. Optionally a second adhesive can be applied over the first layer to form a second adhesive layer thereon. The second adhesive can be the same as the self-etching adhesive or different than the self-etching adhesive. Finally, a dental material can be applied to the dental structure surface having the first adhesive layer and optionally the second adhesive layer  
10 thereon. The dental material can include, for example, a dental restorative, an orthodontic adhesive, or an orthodontic appliance. At least one of the adhesive layers can be hardened under conditions effective to form a bond between the dental material and the dental structure. The adhesive can be hardened before, during, or after applying the dental material. Preferably, the adhesive is  
15 hardened under conditions effective to form a bond between the dental material and the dental structure of at least 7 MPa.

Further, the present invention can be useful for restoring a dental structure. For example, a surface of a dental structure can be wetted with a liquid including an acid-sensitive dye and water prior to applying a self-adhesive  
20 composition to at least a portion of the wet dental structure surface. Preferably, the self-adhesive composition includes at least 40% by weight filler. The application of the self-adhesive composition can cause a visually observable color change in the portion of the dental structure surface having the self-adhesive composition applied thereon. Preferably, the visually observable color  
25 change is from colored to essentially colorless. The self-adhesive composition can be hardened under conditions effective to form a bond between the hardened composition and the dental structure of at least 7 MPa.

Further, the present invention can be useful for adhering an orthodontic appliance to a tooth. For example, a surface of a tooth can be wetted with a  
30 liquid including an acid-sensitive dye and water prior to applying a self-adhesive composition and an orthodontic appliance to at least a portion of the wet tooth surface. In some embodiments, the self-adhesive composition alone is applied to

the wet tooth surface. In other embodiments, an orthodontic appliance having the self-adhesive composition thereon is applied to the wet tooth surface. Optionally, the orthodontic appliance having the self-adhesive composition thereon can be provided as a precoated orthodontic appliance. As an additional  
5 option, the self-adhesive composition can be applied to an adhesive that has been previously coated onto the base of an appliance and previously hardened to form a custom bonding pad or base having a contour that precisely matches the contour of the patient's tooth. The application of the self-adhesive composition can cause a visually observable color change in the portion of the tooth surface  
10 having the self-adhesive composition applied thereon. The self-adhesive composition can be hardened under conditions effective to form a bond between the orthodontic appliance and the tooth.

As yet another option, the self-adhesive composition is applied during an orthodontic bonding procedure using a transfer tray such as the custom transfer  
15 apparatus described in U.S. Pat. Application Serial No. 10/967,797, filed October 18, 2004. In this option, the surface of the patient's teeth are first wetted with a liquid including an acid-sensitive dye and water. Next, a transfer tray having the self-adhesive composition applied to selected areas of the tray is placed over the patient's teeth, with the result that the self-adhesive composition  
20 is transferred to corresponding areas of the patient's teeth. In this embodiment, the self-adhesive composition is a self-etching primer, and the resultant color change provides visual confirmation that the primer has been applied to the selected areas of the patient's teeth. An orthodontic appliance is then bonded to the selected area of each tooth. Preferably, the orthodontic appliance is a  
25 precoated appliance. Optionally, the appliances are placed on the tooth surfaces in an indirect bonding procedure using, for example, the placement device described in U.S. Pat. Application Publication No. 2005/0074716 (Cleary et. al).

Aqueous liquids including an acid-sensitive dye as described herein can also be used as a part of a multi-part dental composition. For example, a multi-  
30 part dental composition can include: a first part including an acid-sensitive dye; and a second part including an acid. Contacting the first part and the second part is effective to cause a color change. Thus, the color change provides an

indication of when the first part and the second part of the multi-part dental composition have been contacted and/or mixed. Preferably, the color change is from colored to essentially colorless. Optionally, the second part includes a self-etching adhesive or a self-adhesive composition.

5           For the convenience of a practitioner, compositions used in methods of the present invention (e.g., aqueous liquids including an acid-sensitive dye) can be provided in kits. In one exemplary embodiment, the kit can include: a liquid including an acid-sensitive dye and water; and a dental etching composition. In another exemplary embodiment, the kit can include: a liquid including an acid-  
10   sensitive dye and water; and a self-etching dental adhesive. In another exemplary embodiment, the kit can include: a liquid including an acid-sensitive dye and water; and a self-adhesive dental composition.

          Objects and advantages of this invention are further illustrated by the  
15   following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention. Unless otherwise indicated, all parts and percentages are on a weight basis, all water is deionized water, and all molecular  
20   weights are weight average molecular weight.

## EXAMPLES

### Test Methods

#### *Adhesion Shear Bond Strength to Enamel or Dentin Test Method*

25           Adhesive shear bond strength to enamel or dentin for a given test sample was evaluated by the following procedure.

*Preparation of Teeth.* Bovine incisal teeth, free of soft tissue, were embedded in circular acrylic disks. The embedded teeth were stored in water in a refrigerator prior to use. In preparation for adhesive testing, the embedded teeth  
30   were ground to expose a flat enamel or dentin surface using 120-grit sandpaper mounted on a lapidary wheel. Further grinding and polishing of the tooth surface



was done using 320-grit sandpaper on the lapidary wheel. The teeth were continuously rinsed with water during the grinding process. The polished teeth were stored in deionized water and used for testing within 2 hours after polishing. The teeth were allowed to warm in a 36°C oven to between room temperature (23°C) and 36°C before use.

*Teeth Treatment.* An adhesive test sample was applied with a dental applicator brush over the entire surface of the prepared enamel or dentin surface according to the specific application techniques detailed in the Examples. After application, the adhesive coating was light cured for 10 seconds with an XL 3000 dental curing light (3M Company, St. Paul, MN). A 2.5-mm thick Teflon mold with a hole approximately 4.7 mm in diameter was clamped to the embedded tooth such that the hole in the mold exposed part of the adhesively prepared tooth surface. A composite material, A2 shade of FILTEK Z250 Universal Restorative (3M Company), was filled into the hole such that the hole was completely filled, but not overfilled, and light cured for 20 seconds to form a "button" that was adhesively attached to the tooth.

*Adhesive Bond Strength Testing.* The adhesive strength of a cured test example was evaluated by mounting the assembly (described above) in a holder clamped in the jaws of an INSTRON testing machine (Instron 4505, Instron Corp. Canton, Massachusetts) with the polished tooth surface oriented parallel to the direction of pull. A loop of orthodontic wire (0.44-mm diameter) was placed around the Z250 button adjacent to the polished tooth surface. The ends of the orthodontic wire were clamped in the pulling jaw of the INSTRON apparatus and pulled at a crosshead speed of 2 mm/min, thereby placing the adhesive bond in shear stress. The force in kilograms (kg) at which the bond failed was recorded, and this number was converted to a force per unit area (units of kg/cm<sup>2</sup> or MPa) using the known surface area of the button. Each reported value of adhesion to enamel or adhesion to dentin represents the average of 2 to 6 replicates.

30

#### Abbreviations, Descriptions, and Sources of Materials

Abbreviation	Description and Source of Material
Rose Bengal	Acid-sensitive dye (Sigma-Aldrich, St. Louis, MO)
TEGDMA	Triethyleneglycol dimethacrylate (Sartomer, Exton, PA)
BisEMA-2	Bisphenol A ethoxylate (2 EO/phenol) dimethacrylate (Sigma-Aldrich)
NPGDMA	Neopentylglycol dimethacrylate (Sigma-Aldrich)
MHP	Methacryloyloxyhexyl phosphate ( $P_2O_5$ derived) (See Preparation Method described herein)
PM-2	KAYAMER PM-2; Bis(methacryloxyethyl) phosphate (Nippon Kiyaku, Japan)
EDMAB	Ethyl 4-(N,N-dimethylamino)benzoate (Sigma-Aldrich)
DPIPF6	Diphenyliodonium hexafluorophosphate (Johnson Matthey, Alpha Aesar Division, Ward Hill, NJ)
CPQ	Camphorquinone (Sigma-Aldrich)
TPA	Triphenyl antimony (Atofina Chemicals, Inc., Philadelphia, PA)
ZrO <sub>2</sub> Filler	Surface-treated zirconia filler (nano-sized primary particles) (See Preparation Method described herein)
RN-50	NOIGEN RN-50 polymerizable nonionic surfactant (DAI -Ichi Kogyo Seiyaku Co. Ltd., Japan; William H. Minkema, MINK Inc., Plymouth, MN)

### Starting Materials Preparations

#### 5 6-Methacryloyloxyhexyl Phosphate (MHP from $P_2O_5$ )

6-Hydroxyhexyl Methacrylate Synthesis: 1,6-Hexanediol (1000.00 g, 8.46 mol, Sigma-Aldrich) was placed in a 1-liter 3-neck flask equipped with a mechanical stirrer and a narrow tube blowing dry air into the flask. The solid diol was heated to 90°C, at which temperature all the solid melted. With continuous stirring, p-toluenesulfonic acid crystals (18.95 g, 0.11 mol) followed by BHT (2.42 g, 0.011 mol) and methacrylic acid (728.49.02 g, 8.46 mol). Heating at 90°C with stirring was continued for 5 hours during which time

vacuum was applied using tap water aspirator for 5-10 minutes after each half-hour reaction time. The heat was turned off and the reaction mixture was cooled to room temperature. The viscous liquid obtained was washed with 10% aqueous sodium carbonate twice (2 x 240 ml), followed by washing with water (2 x 240 ml), and finally with 100 ml of saturated NaCl aqueous solution. The obtained oil was dried using anhydrous Na<sub>2</sub>SO<sub>4</sub> then isolated by vacuum filtration to give 1067 g (67.70 %) of 6-hydroxyhexyl methacrylate, a yellow oil. This desired product was formed along with 15-18% of 1,6-bis(methacryloyloxyhexane). Chemical characterization was by NMR analysis.

10

*6-Methacryloxyhexyl Phosphate Synthesis:* A slurry was formed by mixing P<sub>4</sub>O<sub>10</sub> (178.66 g, 0.63 mol) and methylene chloride (500 ml) in a 1-liter flask equipped with a mechanical stirrer under N<sub>2</sub> atmosphere. The flask was cooled in an ice bath (0-5°C) for 15 minutes. With continuous stirring, 6-hydroxyhexyl methacrylate (962.82 g, which contained 3.78 mol of the mono-methacrylate, along with its dimethacrylate by-product as described above) was added to the flask slowly over 2 hours. After complete addition, the mixture was stirred in the ice bath for 1 hour then at room temperature for 2 hours. BHT (500 mg) was added, and then the temperature was raised to reflux (40-41°C) for 45 minutes. The heat was turned off and the mixture was allowed to cool to room temperature. The solvent was removed under vacuum to afford 1085 g (95.5%) of 6-Methacryloxyhexyl Phosphate as a yellow oil. Chemical characterization was by NMR analysis.

15

20

#### 25 *Surface-Treated ZrO<sub>2</sub> Filler*

Zirconia Sol (217.323 g; 23.5% solids; Nalco, Naperville, IL) was weighed into a plastic flask and then added slowly with vigorous stirring to a solution of mono-2-(methacryloyloxy)ethyl succinate (28.796 g; Sigma-Aldrich) in 1-methoxy-2-propanol (200.001 g; Sigma-Aldrich) that was contained in a plastic flask. The resulting mixture was then dried at 90°C to powder form (dryness) in a convection oven and subsequently ground with a mortar and pestle to a fine powder form for easier later redispersion. Average primary particle size

30

of the zirconia filler was approximately 5 nm, with 50-75 nm loose agglomerates.

*Example 1: Adhesive Application to Tooth and SBS Evaluations*

5           An aqueous dye solution was prepared by dissolving Rose Bengal (7.5 mg) in water (5 g). A microbrush was used to apply the dye solution to a dry tooth surface such that the surface was a visible reddish/pink color. A dental adhesive composition (Adhesive Composition A, Table 1) was then applied by microbrush to the colored, wet tooth surface. Upon contact of the adhesive with  
10   the tooth surface, the surface changed in color from reddish/pink to colorless. The adhesive layer was dried, a second layer of adhesive (Adhesive Composition A) was applied to the dried tooth surface and lightly air-thinned. The tooth surface was then cured for 10 seconds and evaluated 16 hours post-cure for shear bond strength. The initial tooth preparation, curing conditions, and adhesive  
15   bond strength test procedures were as generally described in the Adhesion Shear Bond Strength to Enamel or Dentin Test Method described herein. The resulting SBS testing results were 26.8 MPa to enamel (average of 6 replicates) and 29.9 MPa to dentin (average of 2 replicates).

          Similar SBS values were obtained in identical experiments using only  
20   water (no dye) as the initial application to the tooth surface. These results suggest that the presence of dye in the initial water coating has no effect on bond strength performance.

TABLE 1: Adhesive Composition A	
Component	Amount (grams)
TEGDMA	8.63
BisEMA-2	4.31
NPGDMA	4.31
MHP	0.82
PM-2	8.18
EDMAB	0.22
DPIPF6	0.17
CPQ	0.28
TPA	0.01
ZrO <sub>2</sub> Filler	3.75
RN-50	0.45

*Example 2: Mixing of 2-Part Adhesive Composition:*

- 5            One part of the Rose Bengal aqueous dye solution as described in Example 1 was mixed with two parts of Adhesive Composition A (Table 1). As the two components were contacted and mixed together, the mixture color changed from a reddish/pink to essentially colorless. The color change can be indicative of the thoroughness of mixing. This example demonstrates that an
- 10    acid-sensitive dye can serve as a contact or mixing indicator for an acidic component (e.g., a self-etching adhesive) and a second component that includes the dye.

Various modifications and alterations to this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention. It should be understood that this invention is not intended to be unduly limited by the illustrative embodiments and examples set forth herein and  
5 that such examples and embodiments are presented by way of example only with the scope of the invention intended to be limited only by the claims set forth herein as follows.

What is claimed is:

1. A method for applying a composition to a dental structure, the method comprising:  
wetting a surface of a dental structure with a liquid comprising an acid-sensitive dye and water; and  
applying a composition to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the composition applied thereon, wherein the composition is an etching composition, a self-etching adhesive, a self-adhesive composition, or a combination thereof.
2. The method of claim 1 wherein the visually observable color change is from colored to essentially colorless.
3. The method of claim 1 wherein the visually observable color change is from essentially colorless to colored.
4. The method of claim 1 wherein the visually observable color change is from a first color to a second color, wherein the second color is different than the first color.
5. The method of claim 1 wherein the acid-sensitive dye is selected from the group consisting of Rose Bengal, Bromothymol Blue, Methyl Red, Methyl Orange, Erythrosin B, Eosin Y, and combinations thereof.
6. The method of any of the preceding claims wherein the liquid comprises 0.0001% to 5% by weight of the acid-sensitive dye.
7. The method of any of the preceding claims wherein the liquid further comprises an antibacterial agent, a water soluble monomer, a pH adjuster agent, a buffer, a stabilizer, a surfactant, a fluoride anion, a fluoride releasing agent, or combinations thereof.

8. The method of any of the preceding claims wherein the dental structure comprises enamel, dentin, or cementum.
9. The method of any of the preceding claims wherein the self-etching adhesive is a non-aqueous self-etching adhesive.
10. The method of claim 9 wherein the non-aqueous self-etching adhesive comprises an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, and an initiator system.
11. The method of claim 10 wherein the non-aqueous self-etching adhesive further comprises a filler.
12. The method of any of claims 1 to 8 wherein the self-etching adhesive comprises a water-in-oil emulsion.
13. The method of claim 12 wherein the self-etching adhesive comprises an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, an initiator system, and water.
14. The method of claim 13 wherein the self-etching adhesive further comprises a filler.
15. The method of any of claims 12 to 14 wherein the emulsion is physically stable.
16. The method of any of claims 12 to 15 wherein the self-etching adhesive comprises less than 30% by weight water.
17. The method of any of claims 12 to 16 wherein the emulsion is a water-in-oil micro-emulsion.
18. The method of any of claims 12 to 17 wherein the emulsion is chemically stable.



19. The method of any of claims 1 to 8 wherein the self-adhesive composition is a non-aqueous self-adhesive composition.
20. The method of claim 19 wherein the non-aqueous self-adhesive composition comprises an ethylenically unsaturated compound with acid functionality, an ethylenically unsaturated compound without acid functionality, an initiator system, and at least 40% by weight filler, based on the total weight of the non-aqueous self-adhesive composition.
21. The method of claim 19 or 20 wherein the self-adhesive composition is provided as a precoated orthodontic appliance, and the precoated orthodontic appliance is applied to the wet dental structure surface.
22. The method of claim 21 wherein the orthodontic appliance is selected from the group consisting of a bracket, a buccal tube, a band, a cleat, a button, a lingual retainer, a bite blocker, and combinations thereof.
23. The method of claim 21 or 22 wherein the self-adhesive composition is applied to a surface of an orthodontic appliance to provide a coated orthodontic appliance, and the coated orthodontic appliance is applied to the wet dental structure surface.
24. The method of claim 21 or 22 wherein the self-adhesive composition is provided on an adhesive transfer area of a substrate, and the self-adhesive composition is transferred from the adhesive transfer area of the substrate for applying to the orthodontic appliance.
25. The method of any of claims 10, 11, 13 to 18, or 20 to 24 wherein the acid-functionality comprises carboxylic acid functionality, phosphoric acid functionality, phosphonic acid functionality, sulfonic acid functionality, or combinations thereof.
26. The method of any of claims 10, 11, 13 to 18, or 20 to 25 wherein the non-aqueous self-etching adhesive further comprises a surfactant.

27. A method of bonding a dental material to a dental structure, the method comprising:
- wetting a surface of a dental structure with a liquid comprising an acid-sensitive dye and water;
  - applying a self-etching adhesive to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-etching adhesive applied thereon;
  - drying the dental structure surface to form a first adhesive layer thereon;
  - optionally applying a second adhesive over the first layer to form a second adhesive layer thereon;
  - applying a dental material to the dental structure surface having the first adhesive layer and optionally the second adhesive layer thereon; and
  - hardening at least one of the adhesive layers under conditions effective to form a bond between the dental material and the dental structure.
28. The method of claim 27 wherein the adhesive is hardened under conditions effective to form a bond between the dental material and the dental structure of at least 7 MPa.
29. The method of claim 27 or 28 wherein the adhesive is hardened before, during, or after applying the dental material.
30. The method of any of claims 27 to 29 wherein the second adhesive is the same as the self-etching adhesive.
31. The method of any of claims 27 to 29 wherein the second adhesive is different than the self-etching adhesive.
32. The method of any of claims 27 to 31 wherein the dental material comprises a dental restorative, an orthodontic adhesive, an orthodontic appliance, or a combination thereof.

33. A method of restoring a dental structure, the method comprising:  
wetting a surface of a dental structure with a liquid comprising an acid-sensitive dye and water;  
applying a self-adhesive composition to at least a portion of the wet dental structure surface under conditions effective to cause a visually observable color change in the portion of the dental structure surface having the self-adhesive composition applied thereon; and  
hardening the self-adhesive composition under conditions effective to form a bond between the hardened composition and the dental structure of at least 7 MPa.
34. The method of claim 33 wherein the self-adhesive composition comprises at least 40% by weight filler.
35. A method of adhering an orthodontic appliance to a tooth, the method comprising:  
wetting a surface of a tooth with a liquid comprising an acid-sensitive dye and water;  
applying a self-adhesive composition to at least a portion of the wet tooth surface under conditions effective to cause a visually observable color change in the portion of the tooth surface having the self-adhesive composition applied thereon;  
applying an orthodontic appliance to the tooth surface having the self-adhesive composition applied thereon; and  
hardening the self-adhesive composition under conditions effective to form a bond between the orthodontic appliance and the tooth.
36. The method of claim 35 wherein the self-adhesive composition is a self-etching primer.
37. The method of claim 36 wherein the self-etching primer is applied using a transfer tray.
38. The method of claim 36 wherein the orthodontic appliance is precoated with an orthodontic adhesive.

39. A method of adhering an orthodontic appliance to a tooth, the method comprising:  
wetting a surface of a tooth with a liquid comprising an acid-sensitive dye and water;  
applying an orthodontic appliance having a self-adhesive composition thereon to at least a portion of the wet tooth surface under conditions effective to cause a visually observable color change in the portion of the tooth surface having the orthodontic appliance and self-adhesive composition applied thereon; and  
hardening the self-adhesive composition under conditions effective to form a bond between the orthodontic appliance and the tooth.
40. The method of claim 39 further comprising applying a self-adhesive composition to an orthodontic appliance to provide the orthodontic appliance having the self-adhesive composition thereon.
41. The method of claim 39 wherein the orthodontic appliance having the self-adhesive composition thereon is provided as a precoated orthodontic appliance.
42. A multi-part dental composition comprising:  
a first part comprising an acid-sensitive dye; and  
a second part comprising an acid,  
wherein contacting the first part and the second part is effective to cause a color change.
43. A method for using a multi-part dental composition comprising contacting a first part comprising an acid-sensitive dye and a second part comprising an acid, wherein contacting is effective to cause a color change.
44. The method of claim 43 wherein the color change is from colored to essentially colorless.

45. The method of claim 43 or 44 wherein the second part comprises a self-etching adhesive, a self-adhesive composition, or a combination thereof.
46. A kit comprising:  
a liquid comprising an acid-sensitive dye and water; and  
one or more of a dental etching composition, a self-etching adhesive, and a self-adhesive composition.

## INTERNATIONAL SEARCH REPORT

 International Application No  
 PCT/US2005/024291

 A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 7 A61K6/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)  
 IPC 7 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC, COMPENDEX, BIOSIS, EMBASE

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 204 978 A (GLACE, WILLIAM R ET AL) 27 May 1980 (1980-05-27) figure claims	42-46
A	PALMA, R.G.; TURBINO, M.L.; MATSON, E.; POWERS, J.M.: "Bond strength to dentin with artificial carious lesions: influence of caries detecting dye" AMERICAN JOURNAL OF DENTISTRY, vol. 11, no. 3, 1998, pages 128-130, XP008055059 abstract	1-46

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*G\* document member of the same patent family

Date of the actual completion of the international search

10 November 2005

Date of mailing of the international search report

21/11/2005

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

Thornton, S

## INTERNATIONAL SEARCH REPORT

 International Application No.  
 PCT/US2005/024291

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	KAZEMI, R.B.; MEIERS, J.C.; PEPPERS, K: "Effect of caries disclosing agents on bond strengths of total-etch and self-etching primer dentin bonding systems to resin composite" OPERATIVE DENTISTRY, vol. 27, no. 3, 2002, pages 238-242, XP008054961 the whole document	1-46
A	DE 25 37 463 A1 (DEN-MAT, INC) 22 April 1976 (1976-04-22) claims	1-46
A	US 5 766 012 A (ROSENBAUM ET AL) 16 June 1998 (1998-06-16) examples 2-5 claims	1-46
A	US 4 347 233 A (YAMAUCHI ET AL) 31 August 1982 (1982-08-31) examples claims	1-46
A	PATENT ABSTRACTS OF JAPAN vol. 009, no. 236 (P-390), 21 September 1985 (1985-09-21) & JP 60 089752 A (TOKUYAMA SODA KK), 20 May 1985 (1985-05-20) abstract	1-46
A	WO 02/11642 A (CHIU, PAUL, C) 14 February 2002 (2002-02-14) claims	1-46
P,X	WO 2005/018581 A (3M INNOVATIVE PROPERTIES COMPANY) 3 March 2005 (2005-03-03) page 27, line 29 - page 28, line 22 claims 1-3,127-129	1-46

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US2005/024291

## Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.: —  
because they relate to subject matter not required to be searched by this Authority, namely:  
Although claims 1-41 are directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the composition.
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.  
☐ No protest accompanied the payment of additional search fees.



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2005/024291

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4204978	A	27-05-1980	NONE	
DE 2537463	A1	22-04-1976	JP 51064484 A	03-06-1976
			JP 51067692 A	11-06-1976
US 5766012	A	16-06-1998	NONE	
US 4347233	A	31-08-1982	DE 2948575 A1	12-06-1980
			GB 2036557 A	02-07-1980
			JP 1104745 C	16-07-1982
			JP 55076821 A	10-06-1980
			JP 56048490 B	16-11-1981
JP 60089752	A	20-05-1985	NONE	
WO 0211642	A	14-02-2002	AU 8324601 A	18-02-2002
WO 2005018581	A	03-03-2005	NONE	